

## Aerated concrete

Ingredients	Rate
Quartz sand	60 - 70 %
Portland cement	20 - 30 %
Quicklime	10 - 20 %
Gypsum/Anhydrit	2 - 5 %
Aluminium	0,05 %