

**Plaster, adhesive, reinforcement**

<b>Ingredients in mass-%</b>	<b>Plaster (mineral)</b>	<b>Plaster (synthetic resin trowel)</b>	<b>Adhesive (mineral)</b>	<b>Adhesive (synthetic resin trowel)</b>	<b>Reinforcement (mineral)</b>	<b>Reinforcement (synthetic resin trowel)</b>
Sand (0/2)	20 - 65 %	0 - 15 %	12 - 40 %	12 - 40 %	50 - 65 %	0 - 45 %
Lime stone (milled)	40 - 70 %	40 - 70 %	10 - 50 %	10 - 70 %	0 - 30 %	20 - 70 %
Hydrated lime	5 - 15 %	-	0 - 7 %	0 - 7 %	0 - 1 %	-
Cement	7 - 15 %	-	10 - 30%	10 - 30 %	15 - 30 %	-
Perlite	-	-	0 - 1 %	-	-	0 - 10 %
Aluminium hydroxid	-	-	-	-	-	0 - 10 %
Methyl cellulose	-	-	-	-	-	< 1 %
Styrolacrylat	-	-	-	-	-	0 - 15 %
Copolymer (EVA/VC)	-	10 - 20 %	-	-	0 - 2,5 %	0 - 15 %
Titanium dioxide	-	2 - 5 %	-	-	-	-
Aluminiumhydroxid	-	0 - 8 %	-	-	-	-