

## Perlite

Ingredients	Rate
Silicon dioxide: SiO <sub>2</sub>	70-75%
Aluminium oxide: Al <sub>2</sub> O <sub>3</sub>	12-15%
Sodium oxide: Na <sub>2</sub> O	3-4%
Potassium oxide: K <sub>2</sub> O	3-5%
Iron oxide: Fe <sub>2</sub> O <sub>3</sub>	0.5-2%
Magnesium oxide: MgO	0.2-0.7%
Calcium oxide: CaO	0.5-1.5%
Loss on ignition (chemical / combined water)	3-5%