

Ingredients of concrete, mortar and screed

		Aggregates	Cement	Water	Fly ash	Anhydrite	Expanded glas	Expanded clay	Concrete liquefier
Concrete C 8/10	[kg/m ³]	1840	210	130	0	0	0	0	0
Concrete C 12/15	[kg/m ³]	1836	250	180	50	0	0	0	0
Concrete C 20/25	[kg/m ³]	1850	260	180	80	0	0	0	0
Concrete C 30/37	[kg/m ³]	1824	360	180	0	0	0	0	0
Floor screed (cement)	[kg/m ³]	1585	435	207	0	0	0	0	0
Floor screed (anhydrite)	[kg/m ³]	1421	0	269	0	645	0	0	0
Masonry mortar (MG II a)	[kg/m ³]	1300	210	190	0	0	0	0	0
Masonry mortar (MG III)	[kg/m ³]	1240	280	200	0	0	0	0	0
Light mortar LM 21	[kg/m ³]	1300	210	0	0	0	50	290	3,2